



UNITED STATES WELDING CORPORATION

<p align="center">USW ALLOY DESIGNATION AND DESCRIPTION</p>	<p align="center">TURBALOY® 520 MC-GRADE GTAW SOLID BARE WELDING WIRE IRON BASE</p>	<p align="center">ISO 9001 AS 9100</p>	<p align="center">DATA SHEET 1508</p>																																																
<p align="center">CROSS-REFERENCE CONFORMANCE SPECIFICATIONS</p>	<table border="0"> <tr> <td>MSRR 9500/24</td> <td>BS S143</td> </tr> <tr> <td>FV 520B</td> <td>BAC 46(C)</td> </tr> <tr> <td>USW 1508</td> <td>(Ref AMS 5803, 5825, 5826).</td> </tr> <tr> <td>MSRR 6537</td> <td>14.5Cr 5.5Ni 1.5Cu 1.5Mo .4Cb</td> </tr> </table>			MSRR 9500/24	BS S143	FV 520B	BAC 46(C)	USW 1508	(Ref AMS 5803, 5825, 5826).	MSRR 6537	14.5Cr 5.5Ni 1.5Cu 1.5Mo .4Cb																																								
MSRR 9500/24	BS S143																																																		
FV 520B	BAC 46(C)																																																		
USW 1508	(Ref AMS 5803, 5825, 5826).																																																		
MSRR 6537	14.5Cr 5.5Ni 1.5Cu 1.5Mo .4Cb																																																		
<p align="center">METALLURGICAL BACKGROUND INFORMATION</p>	<p>TURBALOY® 520 is produced by vacuum induction melting and remelting techniques. The final wire is manufactured by special lubricant-free, roller-die forming followed by surface abrasion and cleaning processes.</p> <p>These manufacturing processes ensure consistent metallurgical integrity of the alloy with regard to control of trace elements and physical purity of the welding wire surface.</p> <p>The alloy is a precipitation hardening, martensitic, stainless engineering alloy giving high strength and oxidation resistance. It is used for fabricating base alloys of similar composition.</p>																																																		
<p align="center">MATERIALS TO BE WELDED AND APPLICATIONS</p>	<p>MSRR 6537, 6629, 6596, 6642, 6603, 6596. BS 3146 - ANC 20, HC 101, HC 102. BS S143, S144, S145.</p> <p>Preheat to 212 - 302° F is recommended and PWHT will optimize properties for thick section joints. <i>NOTE:</i> AMS 5825 (17/4 PH) and AMS 5826 (15/5 PH) are also used to weld FV 520B base material.</p>																																																		
<p align="center">WIRE CHEMISTRY WT%</p>	<table border="0"> <tr> <td>Carbon</td> <td>-</td> <td>0.07</td> <td>Molybdenum</td> <td>1.20</td> <td>2.00</td> </tr> <tr> <td>Silicon</td> <td>-</td> <td>0.70</td> <td>Nickel</td> <td>5.00</td> <td>6.00</td> </tr> <tr> <td>Manganese</td> <td>-</td> <td>1.00</td> <td>Copper</td> <td>1.20</td> <td>2.00</td> </tr> <tr> <td>Sulfur</td> <td>-</td> <td>0.020</td> <td>Columbium</td> <td>0.20</td> <td>0.50</td> </tr> <tr> <td>Phosphorus</td> <td>-</td> <td>0.020</td> <td>Oxygen</td> <td>-</td> <td>0.005 (50ppm)</td> </tr> <tr> <td>Chromium</td> <td>13.20</td> <td>14.70</td> <td>Nitrogen</td> <td>-</td> <td>0.0100 (100ppm)</td> </tr> <tr> <td></td> <td></td> <td></td> <td>Hydrogen</td> <td>-</td> <td>0.0010 (10ppm)</td> </tr> <tr> <td></td> <td></td> <td></td> <td>Iron</td> <td></td> <td>Balance</td> </tr> </table>			Carbon	-	0.07	Molybdenum	1.20	2.00	Silicon	-	0.70	Nickel	5.00	6.00	Manganese	-	1.00	Copper	1.20	2.00	Sulfur	-	0.020	Columbium	0.20	0.50	Phosphorus	-	0.020	Oxygen	-	0.005 (50ppm)	Chromium	13.20	14.70	Nitrogen	-	0.0100 (100ppm)				Hydrogen	-	0.0010 (10ppm)				Iron		Balance
Carbon	-	0.07	Molybdenum	1.20	2.00																																														
Silicon	-	0.70	Nickel	5.00	6.00																																														
Manganese	-	1.00	Copper	1.20	2.00																																														
Sulfur	-	0.020	Columbium	0.20	0.50																																														
Phosphorus	-	0.020	Oxygen	-	0.005 (50ppm)																																														
Chromium	13.20	14.70	Nitrogen	-	0.0100 (100ppm)																																														
			Hydrogen	-	0.0010 (10ppm)																																														
			Iron		Balance																																														
<p align="center">WELD PROPERTIES</p>	<p>Hardness (hardened condition) 277- 341 HV</p> <p>Readily weldable</p> <p align="right">Density 7.82 gm/cc</p>																																																		
<p align="center">SIZES AND FORMS AVAILABLE</p>	<table border="0"> <tr> <td align="center">STRAIGHT LENGTHS</td> <td align="center">SPOOLED WIRE</td> </tr> <tr> <td>5 lb. (2.2kg) packs</td> <td>Precision layer wound, with controlled cast and helix</td> </tr> <tr> <td>36" (914mm) lengths</td> <td>12" (300mm) diameter spools standard</td> </tr> <tr> <td>Flag tagged for traceability.</td> <td>8" (200mm), 4" (100mm) and proprietary spool sizes</td> </tr> <tr> <td>(Double tagging and other lengths on request)</td> <td>on request.</td> </tr> <tr> <td>Wide range of diameters.</td> <td>Wide range of diameters and spool weights.</td> </tr> </table>			STRAIGHT LENGTHS	SPOOLED WIRE	5 lb. (2.2kg) packs	Precision layer wound, with controlled cast and helix	36" (914mm) lengths	12" (300mm) diameter spools standard	Flag tagged for traceability.	8" (200mm), 4" (100mm) and proprietary spool sizes	(Double tagging and other lengths on request)	on request.	Wide range of diameters.	Wide range of diameters and spool weights.																																				
STRAIGHT LENGTHS	SPOOLED WIRE																																																		
5 lb. (2.2kg) packs	Precision layer wound, with controlled cast and helix																																																		
36" (914mm) lengths	12" (300mm) diameter spools standard																																																		
Flag tagged for traceability.	8" (200mm), 4" (100mm) and proprietary spool sizes																																																		
(Double tagging and other lengths on request)	on request.																																																		
Wide range of diameters.	Wide range of diameters and spool weights.																																																		
<p align="center">PACKAGING</p>	<p>Sealed, air-evacuated, argon purged Vapor Barrier envelopes with desiccants ensure full protection from atmospheric contamination and prolonged shelf-life.</p>																																																		
<p>DFARS Compliant</p>		<p align="right">www.usweldingcorp.com</p>																																																	