



UNITED STATES WELDING CORPORATION

<p align="center">USW ALLOY DESIGNATION AND DESCRIPTION</p>	<p align="center">TURBALOY® 155 HQ-GRADE GTAW SOLID BARE WELDING WIRE IRON BASE</p>	<p align="center">ISO 9001 AS 9100</p>	<p align="center">DATA SHEET 5794</p>																																										
<p align="center">CROSS-REFERENCE CONFORMANCE SPECIFICATIONS</p>	<table border="0"> <tr> <td>AMS 5794</td> <td>31Fe 21Cr 20Ni 20Co 3.0Mo 2.5W 1.0Cb 0.15N</td> </tr> <tr> <td>N155</td> <td>MSRR 9500/214</td> </tr> <tr> <td>UNS R 30155</td> <td>OMAT 3/166A</td> </tr> <tr> <td>MIL-R-5031 (Comp 9)</td> <td>Multimet Alloy. 20-20-20</td> </tr> <tr> <td>USWC 5794 (A)</td> <td>AISI 661</td> </tr> </table>			AMS 5794	31Fe 21Cr 20Ni 20Co 3.0Mo 2.5W 1.0Cb 0.15N	N155	MSRR 9500/214	UNS R 30155	OMAT 3/166A	MIL-R-5031 (Comp 9)	Multimet Alloy. 20-20-20	USWC 5794 (A)	AISI 661																																
AMS 5794	31Fe 21Cr 20Ni 20Co 3.0Mo 2.5W 1.0Cb 0.15N																																												
N155	MSRR 9500/214																																												
UNS R 30155	OMAT 3/166A																																												
MIL-R-5031 (Comp 9)	Multimet Alloy. 20-20-20																																												
USWC 5794 (A)	AISI 661																																												
<p align="center">METALLURGICAL BACKGROUND INFORMATION</p>	<p>TURBALOY® 155 undergoes a series of proprietary abrading and cleaning processes to remove all surface contaminants. These manufacturing processes ensure a consistent ultra-clean weld wire surface.</p> <p>TURBALOY® 155 is a high temperature, high strength, oxide resisting alloy widely used in the hot section of gas turbine engines. It is used to weld materials of similar composition.</p>																																												
<p align="center">MATERIALS TO BE WELDED AND APPLICATIONS</p>	<p>AMS 5768, 5769, GE B50 A484.</p> <p>AMS 5531, 5532, 5585, 5376.</p> <p>ASTM 639</p>																																												
<p align="center">WIRE CHEMISTRY WT%</p>	<table border="0"> <tr> <td>Carbon</td> <td>-</td> <td>0.10</td> <td>Tantalum</td> <td>-</td> <td>0.05</td> </tr> <tr> <td>Manganese</td> <td>1.00</td> <td>2.00</td> <td>Cobalt</td> <td>18.50</td> <td>21.00</td> </tr> <tr> <td>Silicon</td> <td>-</td> <td>1.00</td> <td>Molybdenum</td> <td>2.5</td> <td>3.5</td> </tr> <tr> <td>Sulfur</td> <td>-</td> <td>0.03</td> <td>Tungsten</td> <td>2.0</td> <td>3.0</td> </tr> <tr> <td>Phosphorus</td> <td>-</td> <td>0.04</td> <td>Columbium</td> <td>0.75</td> <td>1.25</td> </tr> <tr> <td>Chromium</td> <td>20.00</td> <td>22.50</td> <td>Nitrogen</td> <td>0.10</td> <td>0.20</td> </tr> <tr> <td>Nickel</td> <td>19.00</td> <td>21.00</td> <td>Iron</td> <td></td> <td>Balance</td> </tr> </table>			Carbon	-	0.10	Tantalum	-	0.05	Manganese	1.00	2.00	Cobalt	18.50	21.00	Silicon	-	1.00	Molybdenum	2.5	3.5	Sulfur	-	0.03	Tungsten	2.0	3.0	Phosphorus	-	0.04	Columbium	0.75	1.25	Chromium	20.00	22.50	Nitrogen	0.10	0.20	Nickel	19.00	21.00	Iron		Balance
Carbon	-	0.10	Tantalum	-	0.05																																								
Manganese	1.00	2.00	Cobalt	18.50	21.00																																								
Silicon	-	1.00	Molybdenum	2.5	3.5																																								
Sulfur	-	0.03	Tungsten	2.0	3.0																																								
Phosphorus	-	0.04	Columbium	0.75	1.25																																								
Chromium	20.00	22.50	Nitrogen	0.10	0.20																																								
Nickel	19.00	21.00	Iron		Balance																																								
<p align="center">WELD PROPERTIES</p>	<p>Melting Point: 2470°F Density: 8.20gm/cc Hardness of sheet material: Soft condition: 92 HRB, Aged : 94 HRB</p>																																												
<p align="center">SIZES AND FORMS AVAILABLE</p>	<table border="0"> <tr> <td align="center" colspan="2">STRAIGHT LENGTHS</td> <td align="center" colspan="2">SPOOLED WIRE</td> </tr> <tr> <td>5 lb. (2.2kg) packs</td> <td></td> <td>Precision layer wound, with controlled cast and helix</td> <td></td> </tr> <tr> <td>36" (914mm) lengths</td> <td></td> <td>12" (300mm) diameter spools standard</td> <td></td> </tr> <tr> <td>Flag tagged for traceability.</td> <td></td> <td>8" (200mm), 4" (100mm) and proprietary spool sizes</td> <td></td> </tr> <tr> <td>(Double tagging and other lengths on request)</td> <td></td> <td>on request.</td> <td></td> </tr> <tr> <td>Wide range of diameters.</td> <td></td> <td>Wide range of diameters and spool weights.</td> <td></td> </tr> </table>			STRAIGHT LENGTHS		SPOOLED WIRE		5 lb. (2.2kg) packs		Precision layer wound, with controlled cast and helix		36" (914mm) lengths		12" (300mm) diameter spools standard		Flag tagged for traceability.		8" (200mm), 4" (100mm) and proprietary spool sizes		(Double tagging and other lengths on request)		on request.		Wide range of diameters.		Wide range of diameters and spool weights.																			
STRAIGHT LENGTHS		SPOOLED WIRE																																											
5 lb. (2.2kg) packs		Precision layer wound, with controlled cast and helix																																											
36" (914mm) lengths		12" (300mm) diameter spools standard																																											
Flag tagged for traceability.		8" (200mm), 4" (100mm) and proprietary spool sizes																																											
(Double tagging and other lengths on request)		on request.																																											
Wide range of diameters.		Wide range of diameters and spool weights.																																											
<p align="center">PACKAGING</p>	<p>Sealed polyethylene envelopes. (Desiccants optional)</p>																																												
<p>DFARS Compliant</p>		<p align="right">www.usweldingcorp.com</p>																																											